

ForTii® F11

PPA—GF30 FR(40)

30% Glass Fiber Reinforced, PA4T, Electro—friendly, Halogen free and free of red phosphorous, Certified V—0 at 0.2mm

Print Date: 2025—04—10

ForTii® F11 has an excellent balance in flow, toughness and stiffness, enabling thin walls or complicated geometries for E&E applications. F11 is all—color VDE approved, has a high RTI electrical rating of 140°C at 0.75 mm and a CTI ≥800V rating to secure thermal ageing and electrical performance.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.35 / *	%	ISO 294—4
Molding shrinkage (normal)	1.2 / *	%	ISO 294—4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	11500 / 12000	MPa	ISO 527—1/—2
Tensile modulus (—40°C)	12000 / —	MPa	ISO 527—1/—2
Tensile modulus (40°C)	11300 / —	MPa	ISO 527—1/—2
Tensile modulus (80°C)	10800 / 7600	MPa	ISO 527—1/—2
Tensile modulus (100°C)	10000 / —	MPa	ISO 527—1/—2
Tensile modulus (120°C)	8000 / —	MPa	ISO 527—1/—2
Tensile modulus (140°C)	5700	MPa	ISO 527—1/—2
Tensile modulus (160°C)	5000	MPa	ISO 527—1/—2
Stress at break	150 / 140	MPa	ISO 527—1/—2
Stress at break (—40°C)	175 / —	MPa	ISO 527—1/—2
Stress at break (40°C)	145 / —	MPa	ISO 527—1/—2
Stress at break (80°C)	125 / 85	MPa	ISO 527—1/—2
Stress at break (100°C)	115 / —	MPa	ISO 527—1/—2
Stress at break (120°C)	100 / —	MPa	ISO 527—1/—2
Stress at break (140°C)	80	MPa	ISO 527—1/—2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

ForTii® F11

Print Date: 2025-04-10

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Stress at break (160°C)	70	MPa	ISO 527-1/-2
Strain at break	2 / 1.9	%	ISO 527-1/-2
Strain at break (-40°C)	2.2 / -	%	ISO 527-1/-2
Strain at break (40°C)	1.9 / -	%	ISO 527-1/-2
Strain at break (80°C)	1.9 / 2.9	%	ISO 527-1/-2
Strain at break (100°C)	2 / -	%	ISO 527-1/-2
Strain at break (120°C)	2.6 / -	%	ISO 527-1/-2
Strain at break (140°C)	3.3	%	ISO 527-1/-2
Strain at break (160°C)	3.8	%	ISO 527-1/-2
Flexural modulus	11000 / 11500	MPa	ISO 178
Flexural strength	245 / 220	MPa	ISO 178
Flexural modulus (120°C)	8200	MPa	ISO 178
Flexural modulus (160°C)	5000	MPa	ISO 178
Charpy impact strength (+23°C)	50 / 50	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	7.5 / 7.5	kJ/m²	ISO 179/1eA

THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	325 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	305 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.6 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (parallel)	0.3	E-4/°C	ASTM D696
Coeff. of linear therm. expansion (normal)	0.35	E-4/°C	ASTM D696
Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	-	-
Burning Behav. at 3.0 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	V-0 / *	mm	IEC 60695-11-10
UL recognition	3 / *	-	-

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

ForTii[®] F11

Print Date: 2025-04-10

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Relative Temperature Index – electrical	140	°C	UL746B
RTI electrical (Thickness (1) tested)	0.75	mm	UL746B
Thermal Index 5000 hrs	170	°C	IEC 60216/ISO 527-1/-2

ELECTRICAL PROPERTIES	DRY / COND		
Volume resistivity	>1E13 / >1E13	Ohm*m	IEC 62631-3-1
Electric strength	33 / 33	kV/mm	IEC 60243-1
Comparative tracking index	600 / 600	V	IEC 60112
Comparative Tracking Index (above 600V)	875	V	Sim. to IEC 60112
Relative permittivity (100Hz)	4.2 / 4.2	–	IEC 62631-2-1
Relative permittivity (1 MHz)	3.9 / 3.9	–	IEC 62631-2-1
Relative permittivity (1GHz)	3.8 / 3.9	–	IEC 61189-2-721
Relative permittivity (10GHz)	3.8 / 3.9	–	IEC 61189-2-721

OTHER PROPERTIES	DRY / COND		
Humidity absorption	1.6 / *	%	Sim. to ISO 62
Density	1460 / –	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.