

TECHNICAL DATA SHEET

LARIPUR 8025 LARIPUR 8025EG

GENERAL DESCRIPTION

LARIPUR 8025/8025EG is a polyester based TPU. The standard version is designed e.g. for injection moulding of sport soles, wheels, screen elements ,masks and technical items while EG one for the extrusion of hoses, profile, transmission belts and film.

TYPICAL CHEMICAL- PHYSICAL PROPERTIES

The following information is not intended to be used as sales specifications.

Parameter		Typical Value	Unit	Method
Specific Gravity		1.19	gr/cm ³	ASTM D792
Shore Hardness		84	A	ASTM D2240
Abrasion Loss		30	mm ³	DIN 53516
Tensile Modulus	50%	570	psi	ASTM D412
	100%	740		
	300%	2100		
Tensile Strength		7900	psi	ASTM D412
Elongation at Break		600	%	ASTM D412
Tear Strength		95	N/mm	ASTM D624
VICAT Softening Point		163	°F	ASTM D1525

This technical note has been written based on our present best knowledge but the above mentioned data have not to be released as a specification for the material in object.

The properties reported in this Technical Data Sheet are determined on conditioned specimens obtained from injected test plates and represent an average of values gathered from a significant number of production lots.

Even if we guarantee the quality consistency of the LARIPUR products, we could periodically issue updated versions of this Technical Data Sheet and consequently modify the respective sales specifications.

The international standards here indicated have to be intended as a reference to carry out the various tests, but the choice of available options and any possible variation are mentioned in our respective internal standards.

The grades suitable for extrusion are identified with the EG or AE end code and therefore they have to be ordered with such code when used in this application.

STORAGE AND STABILITY

LARIPUR 8025/8025EG is supplied in regular pellet form and it is packaged in 25 kg bags or 500 kg and 1000 kg octabins

LARIPUR 8025/8025EG must be stored in its original and sealed containers and kept in a dry and well ventilated place; avoiding the direct sun radiation.

The shelf life of LARIPUR 8025/8025EG will be 6 months from the date of delivery to the final customer, when stored in its original sealed packaging and in proper conditions

SAFETY

The product is not considered to be dangerous, nevertheless we suggest to read the Material Safety Data Sheet before handling.

PROCESSING RECOMMENDATIONS

Material needs to be dried prior processing at 175-195 °F for 3 hours, preferably using a dehumidifying drier fed by air exhibiting a dew point lower than -22°F.

Suggested moulding temperature profile

Zone	Temperature
Zone 1	355°F
Zone 2	365°F
Zone 3	375°F
Nozzle	365°F

Suggested extrusion temperature profile

Zone	Temperature
Zone 1	375°F
Zone 2	380°F
Zone 3	390°F
Zone 4	385°F
Adapter	375°F
Die	365°F

Being affected by type of machine used, processing conditions and downstream equipment, the temperature profiles as given above has to be considered as just indicative.

Edition: 01 - 06/2016