## Tufnyl® SGF30M(I) Black PA6-GF30

30% Glass Reinforced

Print Date: 2021-11-16

Properties	Typical Data	Unit	Test Method
Dhoological proportion	dry / cond		
Rheological properties			
Molding shrinkage [parallel]	0.3 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	0.9 / *	%	Sim. to ISO 294-4
Mechanical properties	dry / cond		
Tensile modulus	9500 / -	MPa	ISO 527-1/-2
Stress at break	120 / -	MPa	ISO 527-1/-2
Strain at break	2 / -	%	ISO 527-1/-2
Yield stress	120 / -	MPa	ISO 527-1/-2
Yield strain	2 / -	%	ISO 527-1/-2
Flexural modulus	7500 / -	MPa	ISO 178
Flexural strength	180 / -	MPa	ISO 178
Charpy notched impact strength (+23°C)	7 / -	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	6.5 / -	kJ/m²	ISO 180/1A
Thermal properties	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210 / *	°C	ISO 75-1/-2
Other properties	dry / cond		
Water absorption	1.4 / *	%	Sim. to ISO 62
Humidity absorption	0.2 / *	%	Sim. to ISO 62
Density	1360 / -	kg/m³	ISO 1183

Akulon®, Arnitel®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

subject.

Copyright © DSM 2021. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.



## Property Data (Provisional)

## Tufnyl® SGF30M(I) Black

Print Date: 2021-11-16

Properties	Typical Data	Unit	Test Method
Ash content	30	%	ISO 3451

Akulon®, Arnitel®, Arnitel®, EcoPaxX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or that practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

subject.

Copyright © DSM 2021. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

